

Renã;ta Bujã;k

List of Publications by Year in descending order

Source: <https://exaly.com/author-pdf/1705571/publications.pdf>

Version: 2024-02-01

10
papers

166
citations

1684188

5
h-index

1372567

10
g-index

10
all docs

10
docs citations

10
times ranked

210
citing authors

#	ARTICLE	IF	CITATIONS
1	Embedding matrices to extend the shelf life of reference materials 1: Cellulose acetate butyrate. <i>Polymer Degradation and Stability</i> , 2022, 202, 110024.	5.8	1
2	30Âyears of IRMM-1027 reference materials for fissile material accountancy and control: development, production and characterisation. <i>Journal of Radioanalytical and Nuclear Chemistry</i> , 2021, 330, 333-345.	1.5	2
3	Research on long-term stability of mixed U and Pu large-sized dried (LSD) spikes for fissile material control. <i>Progress in Nuclear Science and Technology</i> , 2018, 5, 48-51.	0.3	2
4	Long-term stability of cellulose acetate butyrate thin films for nuclear certified reference materials. <i>Journal of Radioanalytical and Nuclear Chemistry</i> , 2017, 311, 877-886.	1.5	7
5	Results of the REIMEP-17 interlaboratory comparison for the measurement of the U and Pu amount content and isotope amount ratios in the synthetic dissolved spent nuclear fuel solution. <i>Accreditation and Quality Assurance</i> , 2015, 20, 421-429.	0.8	3
6	Effects of some mineral additions to Portland cement on reinforcement corrosion. <i>Cement and Concrete Research</i> , 2013, 53, 59-67.	11.0	81
7	Development and application of the in situ radiotracer thin gap method for the investigation of corrosion processes. I. Adaptation of the thin gap method for the application of porous surfaces. <i>Electrochimica Acta</i> , 2013, 109, 468-474.	5.2	3
8	Preparation and electrochemical characterization of low-index rhodium single crystal electrodes in sulfuric acid. <i>Electrochimica Acta</i> , 2009, 54, 5509-5521.	5.2	33
9	Accumulation of uranium on austenitic stainless steel surfaces. <i>Electrochimica Acta</i> , 2007, 52, 2542-2551.	5.2	23
10	In situ radiotracer and voltammetric study of the formation of surface adlayers in the course of Cr(VI) reduction on polycrystalline and (111) oriented platinum. <i>Electrochimica Acta</i> , 2006, 52, 332-341.	5.2	11