

Divino Eterno Teixeira

List of Publications by Year in descending order

Source: <https://exaly.com/author-pdf/215184/publications.pdf>

Version: 2024-02-01

8
papers

71
citations

1937685
4
h-index

1872680
6
g-index

8
all docs

8
docs citations

8
times ranked

94
citing authors

| # | ARTICLE | IF | CITATIONS |
|---|---|-----|-----------|
| 1 | Utilization of the coconut shell of babaçu (Orbignya sp.) to produce cement-bonded particleboard. Bioresource Technology, 2002, 85, 159-163. | 9.6 | 48 |
| 2 | Adhesivity of Bio-Based Anhydrous Citric Acid, Tannin-Citric Acid and Ricinoleic Acid in the Properties of Formaldehyde-Free Medium Density Particleboard (MDP). Drvna Industrija, 2020, 71, 235-242. | 0.6 | 9 |
| 3 | Color variation of rubberwood clones and cypress infected by Gloeophyllum striatum and Phanerochaete chrysosporium. International Biodeterioration and Biodegradation, 2009, 63, 41-45. | 3.9 | 6 |
| 4 | Technological Characterization of Cupressus spp. Wood. Floresta E Ambiente, 2010, 17, 1-11. | 0.4 | 5 |
| 5 | Resistência à abrasão, dureza Janka e a correlação com outras propriedades em 14 espécies de madeiras tropicais brasileiras com potencial para utilização em pisos de madeira. Ciência Da Madeira, 2019, 10, 135-141. | 0.3 | 2 |
| 6 | My Wooden House: Unit Cost of Popular Housing in Acre state, Brazil. Floresta E Ambiente, 2019, 26, . | 0.4 | 1 |
| 7 | Asbestos-free autoclaved wood fiber-cement sheets from recycled old corrugated containers and kraft pulp of Douglas fir: properties and scanning electron microscopy. Maderas: Ciencia Y Tecnologia, 2018, , 0-0. | 0.7 | 0 |
| 8 | MEDIUM DENSITY PARTICLEBOARD USING POSTHARVEST SUGARCANE LEAF STRAW: EFFECT OF RESIN TYPE AND CONTENT, DENSITY AND LAYERS ARRANGEMENT. Floresta, 2021, 51, 576. | 0.2 | 0 |