

Yuyang Tian

List of Publications by Year in descending order

Source: <https://exaly.com/author-pdf/3269465/publications.pdf>

Version: 2024-02-01

48
papers

2,859
citations

201575

27
h-index

197736

49
g-index

52
all docs

52
docs citations

52
times ranked

3152
citing authors

#	ARTICLE	IF	CITATIONS
1	Frustrated Lewis pairs in situ formation in B-based porous aromatic frameworks for efficient o-phenylenediamine cyclization. <i>Chinese Chemical Letters</i> , 2023, 34, 107559.	4.8	3
2	High energy and insensitive explosives based on energetic porous aromatic frameworks. <i>Nano Research</i> , 2022, 15, 1698-1705.	5.8	9
3	Continuous Porous Aromatic Framework Membranes with Modifiable Sites for Optimized Gas Separation. <i>Angewandte Chemie - International Edition</i> , 2022, 61, .	7.2	19
4	Stable metal-organic framework fixing within zeolite beads for effectively static and continuous flow degradation of tetracycline by peroxymonosulfate activation. <i>Chemical Engineering Journal</i> , 2022, 435, 134916.	6.6	49
5	Fine-tuned mesoporous covalent organic frameworks for highly efficient low molecular-weight proteins separation. <i>Nano Research</i> , 2022, 15, 4569-4574.	5.8	12
6	Porous Cationic Electrospun Fibers with Sufficient Adsorption Sites for Effective and Continuous UO_2^{2+} Uptake. <i>Advanced Functional Materials</i> , 2022, 32, .	7.8	34
7	Innentitelbild: Continuous Porous Aromatic Framework Membranes with Modifiable Sites for Optimized Gas Separation (<i>Angew. Chem.</i> 1/2022). <i>Angewandte Chemie</i> , 2022, 134, .	1.6	0
8	Facile synthesis of porphyrin-based PAF membrane for hydrogen purification. <i>Inorganic Chemistry Communication</i> , 2022, 141, 109526.	1.8	4
9	Au Nanoparticles Supported by Porous Aromatic Frameworks as Efficient and Recyclable Catalysts for Nitro Reduction. <i>Catalysts</i> , 2022, 12, 588.	1.6	2
10	Turning Electronic Waste to Continuous-Flow Reactor Using Porous Aromatic Frameworks. <i>ACS Applied Materials & Interfaces</i> , 2022, 14, 25601-25608.	4.0	7
11	Two flexible cationic metal-organic frameworks with remarkable stability for CO ₂ /CH ₄ separation. <i>Nano Research</i> , 2021, 14, 3288-3293.	5.8	15
12	A carbazole-grafted covalent organic framework as turn-on fluorescence chemosensor for recognition and detection of Pb ²⁺ ions with high selectivity and sensitivity. <i>Journal of Materials Science</i> , 2021, 56, 11789-11800.	1.7	25
13	Coumarin-embedded MOF UiO-66 as a selective and sensitive fluorescent sensor for the recognition and detection of Fe ³⁺ ions. <i>Journal of Materials Chemistry C</i> , 2021, 9, 16978-16984.	2.7	32
14	Unusual design strategy for a stable and soluble high-molecular-weight copper(II) arylacetylide polymer. <i>Chemical Communications</i> , 2021, 57, 12004-12007.	2.2	1
15	Uniform and stable immobilization of metal-organic frameworks into chitosan matrix for enhanced tetracycline removal from water. <i>Chemical Engineering Journal</i> , 2020, 382, 122893.	6.6	258
16	Highly selective reduction of nitroarenes with gold nano-catalysts immobilized in porous aromatic frameworks. <i>Microporous and Mesoporous Materials</i> , 2020, 306, 110393.	2.2	11
17	Hydroxyl porous aromatic frameworks for efficient adsorption of organic micropollutants in water. <i>RSC Advances</i> , 2020, 10, 26335-26341.	1.7	10
18	Porous Aromatic Framework with Tailored Binding Sites and Pore Sizes as a High-Performance Hemoperfusion Adsorbent for Bilirubin Removal. <i>Advanced Science</i> , 2020, 7, 2001899.	5.6	47

#	ARTICLE	IF	CITATIONS
19	Efficient Gold Recovery from E-Waste via a Chelate-Containing Porous Aromatic Framework. <i>ACS Applied Materials & Interfaces</i> , 2020, 12, 30474-30482.	4.0	69
20	Anion Substitution in Porous Aromatic Frameworks: Boosting Molecular Permeability and Selectivity for Membrane Acetylene Separation. <i>Advanced Materials</i> , 2020, 32, e1907449.	11.1	34
21	Porous Aromatic Frameworks (PAFs). <i>Chemical Reviews</i> , 2020, 120, 8934-8986.	23.0	389
22	The fabrication of IMo ₆ @iPAF-1 as an enzyme mimic in heterogeneous catalysis for oxidative desulfurization under O ₂ or air. <i>Journal of Materials Chemistry A</i> , 2020, 8, 9813-9824.	5.2	23
23	Synergic Catalysts of Polyoxometalate@Cationic Porous Aromatic Frameworks: Reciprocal Modulation of Both Capture and Conversion Materials. <i>Advanced Materials</i> , 2019, 31, e1902444.	11.1	65
24	An electrospun fiber based metal-organic framework composite membrane for fast, continuous, and simultaneous removal of insoluble and soluble contaminants from water. <i>Journal of Materials Chemistry A</i> , 2019, 7, 22559-22570.	5.2	89
25	Understanding the desulphurization process in an ionic porous aromatic framework. <i>Chemical Science</i> , 2019, 10, 606-613.	3.7	47
26	PAF-1@cellulose nanofibril composite aerogel for highly-efficient removal of bisphenol A. <i>Journal of Materials Chemistry A</i> , 2019, 7, 157-164.	5.2	41
27	Fluorescein-based fluorescent porous aromatic framework for Fe ³⁺ detection with high sensitivity. <i>Journal of Materials Chemistry C</i> , 2019, 7, 2327-2332.	2.7	75
28	Polarity engineering of porous aromatic frameworks for specific water contaminant capture. <i>Journal of Materials Chemistry A</i> , 2019, 7, 2507-2512.	5.2	45
29	Pore-size dominated electrochemical properties of covalent triazine frameworks as anode materials for K-ion batteries. <i>Chemical Science</i> , 2019, 10, 7695-7701.	3.7	84
30	Porous Aromatic Framework Modified Electrospun Fiber Membrane as a Highly Efficient and Reusable Adsorbent for Pharmaceuticals and Personal Care Products Removal. <i>ACS Applied Materials & Interfaces</i> , 2019, 11, 16662-16673.	4.0	59
31	Dual luminescent covalent organic frameworks for nitro-explosive detection. <i>Journal of Materials Chemistry A</i> , 2019, 7, 27148-27155.	5.2	108
32	Size, Shape, and Porosity Control of Medi-MOF-1 via Growth Modulation under Microwave Heating. <i>Crystal Growth and Design</i> , 2019, 19, 889-895.	1.4	29
33	A mineralized cell-based functional platform: construction of yeast cells with biogenetic intracellular hydroxyapatite nanoscaffolds. <i>Nanoscale</i> , 2018, 10, 3489-3496.	2.8	14
34	Task-specific design of a hierarchical porous aromatic framework as an ultrastable platform for large-sized catalytic active site binding. <i>Chemical Communications</i> , 2018, 54, 1603-1606.	2.2	25
35	A Crystalline Polyimide Porous Organic Framework for Selective Adsorption of Acetylene over Ethylene. <i>Journal of the American Chemical Society</i> , 2018, 140, 15724-15730.	6.6	207
36	Construction of Porous Aromatic Frameworks with Exceptional Porosity via Building Unit Engineering. <i>Advanced Materials</i> , 2018, 30, e1804169.	11.1	66

#	ARTICLE	IF	CITATIONS
37	Fabrication of triazine-based Porous Aromatic Framework (PAF) membrane with structural flexibility for gas mixtures separation. <i>Journal of Industrial and Engineering Chemistry</i> , 2018, 67, 373-379.	2.9	21
38	Construction of Thermophilic Lipase-Embedded Metal-Organic Frameworks via Biomimetic Mineralization: A Biocatalyst for Ester Hydrolysis and Kinetic Resolution. <i>ACS Applied Materials & Interfaces</i> , 2016, 8, 24517-24524.	4.0	197
39	Coupling fullerene into porous aromatic frameworks for gas selective sorption. <i>Chemical Science</i> , 2016, 7, 3751-3756.	3.7	42
40	Targeted Syntheses of Charged Porous Aromatic Frameworks for Iodine Enrichment and Release. <i>Acta Chimica Sinica</i> , 2016, 74, 67.	0.5	6
41	Highly Efficient Enrichment of Volatile Iodine by Charged Porous Aromatic Frameworks with Three Sorption Sites. <i>Angewandte Chemie - International Edition</i> , 2015, 54, 12733-12737.	7.2	327
42	Syntheses and characterizations of two curcumin-based cocrystals. <i>Inorganic Chemistry Communication</i> , 2015, 55, 92-95.	1.8	29
43	Ionic Liquid assisted Synthesis of Zeolite-ION. <i>Zeitschrift Fur Anorganische Und Allgemeine Chemie</i> , 2014, 640, 1177-1181.	0.6	15
44	Synthesis and structural characterization of a single-crystal to single-crystal transformable coordination polymer. <i>Dalton Transactions</i> , 2014, 43, 1519-1523.	1.6	15
45	Targeted synthesis of micro-mesoporous hybrid material derived from octaphenylsilsesquioxane building units. <i>Microporous and Mesoporous Materials</i> , 2013, 165, 92-98.	2.2	40
46	Facile synthesis of ZIF-8 nanocrystals in eutectic mixture. <i>CrystEngComm</i> , 2012, 14, 8365.	1.3	25
47	Synthesis of a SAPO-34 membrane on macroporous supports for high permeance separation of a CO ₂ /CH ₄ mixture. <i>Journal of Materials Chemistry</i> , 2009, 19, 7698.	6.7	63
48	Continuous Porous Aromatic Framework Membranes with Modifiable Sites for Optimized Gas Separation. <i>Angewandte Chemie</i> , 0, , .	1.6	1