

Igor Zibrov

List of Publications by Year in descending order

Source: <https://exaly.com/author-pdf/3332868/publications.pdf>

Version: 2024-02-01

14

papers

72

citations

1684188

5

h-index

1588992

8

g-index

14

all docs

14

docs citations

14

times ranked

101

citing authors

#	ARTICLE	IF	CITATIONS
1	Magnetic, electronic, and transport properties of the high-pressure-synthesized chiral magnets Mn _{1-x} R _x Ge. <i>Physical Review B</i> , 2018, 98, .	3.2	13
2	High-pressure, high-temperature study of GeS ₂ and GeSe ₂ . <i>Inorganic Materials</i> , 2014, 50, 768-774.	0.8	8
3	Behavior of detonation nanodiamond at high pressures and temperatures in the presence of a hydrogen-containing fluid. <i>Inorganic Materials</i> , 2016, 52, 351-356.	0.8	8
4	Structural and morphological transformations of carbon nanospheres during high-temperature, high-pressure processing. <i>Inorganic Materials</i> , 2017, 53, 462-468.	0.8	7
5	Nanostructured compacts and composites based on diamond-like boron nitride. <i>Inorganic Materials: Applied Research</i> , 2017, 8, 551-555.	0.5	6
6	V ₃ O ₄ 7O ₇ , a new high-pressure oxide with the simpsonite structure. <i>Inorganic Materials</i> , 2016, 52, 902-908.	0.8	5
7	Luminescence properties of diamond prepared in the presence of rare-earth elements. <i>Inorganic Materials</i> , 2017, 53, 809-815.	0.8	4
8	Direct Evidence of Catalytic Role of Boron in Graphiteâ€¢toâ€¢Diamond Solidâ€¢Phase Conversion under High Pressure. <i>Physica Status Solidi - Rapid Research Letters</i> , 2020, 14, 2000247.	2.4	4
9	Physical properties of $\text{Mn}_{1-x}\text{Fe}_x\text{O}$. <i>Physica Status Solidi - Rapid Research Letters</i> , 2020, 14, 2000247.	3.2	4
10	New Pressure-Induced Phase Transitions in Bismuthinite. <i>JETP Letters</i> , 2021, 114, 470-474.	1.4	4
11	Heterographene BCN phase prepared at high pressures and temperatures: Formation kinetics, structure, and properties. <i>Inorganic Materials</i> , 2014, 50, 349-357.	0.8	3
12	Dualism of the YbCoC. <i>Physical Review B</i> , 2020, 101, .	3.2	3
13	High-Pressure Synthesis of H ₂ â€“ Ta ₂ O ₆ â€“ 0.5x Å· 2/3H ₂ O (0 â‰ x â‰ 2) with the Hexagonal Tungsten Bronze Structure. <i>Inorganic Materials</i> , 2019, 55, 489-494.	0.8	2
14	Synthesis of Microcrystals of Heavy-Boron-Doped Diamond and BC ₃ -Heterodiamonds at High Pressures and Temperatures. <i>Glass and Ceramics (English Translation of Steklo I Keramika)</i> , 2019, 75, 441-445.	0.6	1