

Angelina Solodovnik

List of Publications by Year in descending order

Source: <https://exaly.com/author-pdf/459145/publications.pdf>

Version: 2024-02-01

16
papers

47
citations

1937685

4
h-index

1720034

7
g-index

16
all docs

16
docs citations

16
times ranked

18
citing authors

#	ARTICLE	IF	CITATIONS
1	Phase states and the mechanism of crystallization of condensed Ar~Kr mixtures. Low Temperature Physics, 2021, 47, 874-880.	0.6	0
2	Structure and properties of Ar~Kr solid solutions. Low Temperature Physics, 2019, 45, 545-550.	0.6	3
3	Structural transformations in N2~Kr alloys. Low Temperature Physics, 2019, 45, 1296-1300.	0.6	0
4	Structure of N2-CH4 cryoalloys. Low Temperature Physics, 2017, 43, 1399-1404.	0.6	3
5	Unusual morphology of equimolar Ar~Kr alloys. Low Temperature Physics, 2015, 41, 424-428.	0.6	2
6	Cluster approach to formation of nitrogen~rare gas cryoalloys. Low Temperature Physics, 2013, 39, 456-459.	0.6	4
7	Orientalional order parameter in CO2~Kr solid solutions. Low Temperature Physics, 2010, 36, 1094-1099.	0.6	2
8	Lattice parameters of CO2-Kr cryoalloys. Low Temperature Physics, 2010, 36, 254-259.	0.6	4
9	Structure of nitrous oxide-carbon dioxide alloys. Low Temperature Physics, 2009, 35, 339-342.	0.6	2
10	Orientalional order parameter in CO2-based alloys with rare gases from THEED data: pure CO2. Low Temperature Physics, 2007, 33, 600-605.	0.6	7
11	Structural peculiarities of quench-condensed pure and argon-doped nitrous oxide. Low Temperature Physics, 2003, 29, 788-791.	0.6	1
12	Effect of an orientational phase transformation on low-temperature creep in n-H2. Low Temperature Physics, 2001, 27, 949-951.	0.6	1
13	Orientalional Order in Solid N2O-Kr Solutions. Journal of Low Temperature Physics, 2001, 122, 493-499.	1.4	1
14	Structure and lattice parameters of thin C60 films. Low Temperature Physics, 1999, 25, 220-224.	0.6	3
15	The structure and the orientational order parameter of Ar~CO2 solid solutions. Low Temperature Physics, 1998, 24, 669-678.	0.6	13
16	Orientalional order/disorder in CO2~Ar solid mixtures. European Physical Journal D, 1996, 46, 521-522.	0.4	1