
Zhiming Mi

List of Publications by Year in descending order

Source: https://exaly.com/author-pdf/519518/publications.pdf Version: 2024-02-01



німілс Мі

#	Article	IF	CITATIONS
1	Thin-film composite nanofiltration membranes with poly (amidoxime) as organic interlayer for effective desalination. Journal of Environmental Chemical Engineering, 2022, 10, 107015.	3.3	9
2	Polyamidoxime grafting on ultrahigh-strength cellulose-based jute fabrics for effectively extracting uranium from seawater. New Journal of Chemistry, 2022, 46, 6296-6306.	1.4	4
3	Regulating the morphology of nanofiltration membrane by thermally induced inorganic salt crystals for efficient water purification. Journal of Membrane Science, 2021, 617, 118645.	4.1	20
4	Positively charged nanofiltration membrane prepared by polydopamine deposition followed by crosslinking for high efficiency cation separation. Polymer Testing, 2021, 93, 107000.	2.3	19
5	Soluble copolyimides containing 4,4′-isopropylidenedicyclohexanol (HBPA) isomer units: Synthesis, characterization, thermal, mechanical, and optical properties. High Performance Polymers, 2020, 32, 406-417.	0.8	2
6	PEEK composites with polyimide sizing SCF as reinforcement: Preparation, characterization, and mechanical properties. High Performance Polymers, 2020, 32, 383-393.	0.8	12
7	Improving the Interfacial Adhesion of Carbon Fiber/Polyether Ether Ketone Composites by Polyimide Coating. ChemistrySelect, 2020, 5, 5507-5514.	0.7	9
8	A carboxyl potassium salt polysulfone (PSF-COOK)-embedded mixed matrix membrane with high permeability and anti-fouling properties for the effective separation of dyes and salts. Applied Surface Science, 2019, 490, 7-17.	3.1	36
9	Soluble Polyimides Bearing (cis, trans)-Hydrogenated Bisphenol A and (trans, trans)-Hydrogenated Bisphenol A Moieties: Synthesis, Properties and the Conformational Effect. Polymers, 2019, 11, 854.	2.0	9
10	A New Tetrasubstituted Imidazole Based Difunctional Probe for UV-spectrophotometric and Fluorometric Detecting of Fe3+ Ion in Aqueous Solution. Chemical Research in Chinese Universities, 2019, 35, 200-208.	1.3	6
11	Novel copolyimides containing 1,4:3,6-dianhydro- <scp>d</scp> -mannitol unit Preparation, characterization, thermal, mechanical, soluble, and optical properties. High Performance Polymers, 2019, 31, 220-229.	0.8	8
12	The influence of sulfonated hyperbranched polyethersulfone-modified halloysite nanotubes on the compatibility and water separation performance of polyethersulfone hybrid ultrafiltration membranes. Journal of Membrane Science, 2018, 557, 13-23.	4.1	57
13	Transparent and soluble polyimide films from 1,4:3,6-dianhydro-D-mannitol based dianhydride and diamines containing aromatic and semiaromatic units: Preparation, characterization, thermal and mechanical properties. Polymer Degradation and Stability, 2018, 151, 80-89.	2.7	38
14	Transparent and soluble polyimide films containing 4,4′â€isopropylidenedicyclohexanol (<i>Cis</i> â€HBPA) units: Preparation, characterization, thermal, mechanical, and dielectric properties. Journal of Polymer Science Part A, 2018, 56, 2115-2128.	2.5	16
15	Synthesis of Highly Sensitive Fluorescent Probe Based on Tetrasubstituted Imidazole and Its Application for Selective Detection of Ag+ Ion in Aqueous Media. Chemical Research in Chinese Universities, 2018, 34, 369-374.	1.3	10
16	Influence of 1:4;3:6-dianhydro-d- mannitol-based polyamide as an additive on morphology, permeability and antifouling performance of PES ultrafiltration membrane. High Performance Polymers, 2018, 30, 1147-1158.	0.8	0
17	Preparation of hydrophilic and antifouling polysulfone ultrafiltration membrane derived from phenolphthalin by copolymerization method. Applied Surface Science, 2017, 401, 69-78.	3.1	65
18	Soluble polyimides containing 1,4:3,6â€dianhydroâ€dâ€glucidol and fluorinated units: Preparation, characterization, optical, and dielectric properties. Journal of Polymer Science Part A, 2017, 55, 3253-3265.	2.5	47

#	Article	IF	CITATIONS
19	Synthesis, characterization and evaluation of dewatering properties of chitosan-grafting DMDAAC flocculants. International Journal of Biological Macromolecules, 2016, 92, 761-768.	3.6	74