

# Hoi Ri Moon

## List of Publications by Year in descending order

Source: <https://exaly.com/author-pdf/5730430/publications.pdf>

Version: 2024-02-01

74  
papers

5,346  
citations

126907

33  
h-index

82547

72  
g-index

77  
all docs

77  
docs citations

77  
times ranked

7583  
citing authors

#	ARTICLE	IF	CITATIONS
1	Tetrazole-Based Energetic Metal-Organic Frameworks: Impacts of Metals and Ligands on Explosive Properties. <i>European Journal of Inorganic Chemistry</i> , 2022, 2022, .	2.0	7
2	Modulating Energetic Characteristics of Multicomponent 1D Coordination Polymers: Interplay of Metal-Ligand Coordination Modes. <i>Inorganic Chemistry</i> , 2022, 61, 1881-1887.	4.0	5
3	Post-synthetic ligand cyclization in metal-organic frameworks through functional group connection with regioisomerism. <i>Chemical Communications</i> , 2022, 58, 5948-5951.	4.1	5
4	Metal-Organic Frameworks: Special Collection 2020. <i>Chemistry - A European Journal</i> , 2022, 28, e202200607.	3.3	0
5	Thermodynamic Separation of Hydrogen Isotopes Using Hofmann-Type Metal-Organic Frameworks with High-Density Open Metal Sites. <i>ACS Applied Materials &amp; Interfaces</i> , 2022, 14, 30946-30951.	8.0	15
6	Dynamic Variation of Responsive Metal-Organic Frameworks toward Specific Stimuli. <i>Bulletin of Japan Society of Coordination Chemistry</i> , 2022, 79, 50-57.	0.2	0
7	Interface-Sensitized Chemiresistor: Integrated Conductive and Porous Metal-Organic Frameworks. <i>Chemical Engineering Journal</i> , 2022, 449, 137780.	12.7	14
8	Solid-state phase transformations toward a metal-organic framework of 7-connected Zn <sub>4</sub> O secondary building units. <i>Nano Research</i> , 2021, 14, 411-416.	10.4	4
9	High performance H <sub>2</sub> O <sub>2</sub> production achieved by sulfur-doped carbon on CdS photocatalyst via inhibiting reverse H <sub>2</sub> O <sub>2</sub> decomposition. <i>Applied Catalysis B: Environmental</i> , 2021, 284, 119690.	20.2	69
10	Synthesis of MOF-on-MOF architectures in the context of interfacial lattice matching. <i>CrystEngComm</i> , 2021, 23, 2337-2354.	2.6	27
11	Nanocomposite synthesis strategies based on the transformation of well-tailored metal-organic frameworks. <i>Chemical Communications</i> , 2021, 57, 6960-6974.	4.1	5
12	Hydrogen separation and purification with MOF-based materials. <i>Materials Chemistry Frontiers</i> , 2021, 5, 4022-4041.	5.9	23
13	Non-stackable molecules assemble into porous crystals displaying concerted cavity-changing motions. <i>Chemical Science</i> , 2021, 12, 6378-6384.	7.4	7
14	Elucidation of Diffusivity of Hydrogen Isotopes in Flexible MOFs by Quasi-Elastic Neutron Scattering. <i>Advanced Materials</i> , 2021, 33, e2007412.	21.0	16
15	<sc>MOF-on-MOF</sc> Architectures: Applications in Separation, Catalysis, and Sensing. <i>Bulletin of the Korean Chemical Society</i> , 2021, 42, 956-969.	1.9	85
16	Mechanochemistry as a Reconstruction Tool of Decomposed Metal-Organic Frameworks. <i>Inorganic Chemistry</i> , 2021, 60, 11825-11829.	4.0	11
17	Alterations to secondary building units of metal-organic frameworks for the development of new functions. <i>Inorganic Chemistry Frontiers</i> , 2020, 7, 12-27.	6.0	60
18	Porous and Nonporous Coordination Polymers Induced by Pseudohalide Ions for Luminescence and Gas Sorption. <i>Inorganic Chemistry</i> , 2020, 59, 15987-15999.	4.0	18

#	ARTICLE	IF	CITATIONS
19	Structural evolution of ZIF-67-derived catalysts for furfural hydrogenation. <i>Journal of Catalysis</i> , 2020, 392, 302-312.	6.2	25
20	Dual-fixations of europium cations and TEMPO species on metal-organic frameworks for the aerobic oxidation of alcohols. <i>Dalton Transactions</i> , 2020, 49, 8060-8066.	3.3	12
21	Pore engineering of metal-organic frameworks with coordinating functionalities. <i>Coordination Chemistry Reviews</i> , 2020, 420, 213377.	18.8	75
22	Specific Isotope-Responsive Breathing Transition in Flexible Metal-Organic Frameworks. <i>Journal of the American Chemical Society</i> , 2020, 142, 13278-13282.	13.7	47
23	Surface-Deactivated Core-Shell Metal-Organic Framework by Simple Ligand Exchange for Enhanced Size Discrimination in Aerobic Oxidation of Alcohols. <i>Chemistry - A European Journal</i> , 2020, 26, 7568-7572.	3.3	34
24	Computer-aided discovery of connected metal-organic frameworks. <i>Nature Communications</i> , 2019, 10, 3620.	12.8	71
25	Hydrogen Isotope Separation in Confined Nanospaces: Carbons, Zeolites, Metal-Organic Frameworks, and Covalent Organic Frameworks. <i>Advanced Materials</i> , 2019, 31, e1805293.	21.0	98
26	Tuning of the flexibility in metal-organic frameworks based on pendant arm macrocycles. <i>Chemical Communications</i> , 2019, 55, 8832-8835.	4.1	16
27	Coordinated Molecule-Modulated Magnetic Phase with Metamagnetism in Metal-Organic Frameworks. <i>Inorganic Chemistry</i> , 2019, 58, 8895-8899.	4.0	17
28	Isotope Separation: Hydrogen Isotope Separation in Confined Nanospaces: Carbons, Zeolites, Metal-Organic Frameworks, and Covalent Organic Frameworks ( <i>Adv. Mater.</i> 20/2019). <i>Advanced Materials</i> , 2019, 31, 1970147.	21.0	15
29	Elucidation of flexible metal-organic frameworks: Research progresses and recent developments. <i>Coordination Chemistry Reviews</i> , 2019, 389, 161-188.	18.8	163
30	Versatile Processing of Metal-Organic Framework-Fluoropolymer Composite Inks with Chemical Resistance and Sensor Applications. <i>ACS Applied Materials &amp; Interfaces</i> , 2019, 11, 4385-4392.	8.0	29
31	Modelling of adsorption and intercalation of hydrogen on/into tungsten disulphide multilayers and multiwall nanotubes. <i>Physical Chemistry Chemical Physics</i> , 2018, 20, 12061-12074.	2.8	6
32	Three-dimensional iron(II) porous coordination polymer exhibiting carbon dioxide-dependent spin crossover. <i>Chemical Communications</i> , 2018, 54, 4262-4265.	4.1	29
33	Structural diversity of metal-organic frameworks via employment of azamacrocycles as a building block. <i>Journal of Inclusion Phenomena and Macrocyclic Chemistry</i> , 2018, 92, 237-249.	1.6	16
34	Hierarchically porous adamantane-shaped carbon nanoframes. <i>Journal of Materials Chemistry A</i> , 2018, 6, 18906-18911.	10.3	29
35	Single-crystal-to-single-crystal transformation of a coordination polymer from 2D to 3D by [2 + 2] photodimerization assisted by a coexisting flexible ligand. <i>CrystEngComm</i> , 2017, 19, 3719-3722.	2.6	13
36	Facile Synthesis and Characterization of Nanostructured Transition Metal/Ceria Solid Solutions (TM <sub>x</sub> Ce <sub>1-x</sub> O <sub>2</sub> ) for CO Oxidation. <i>Chemistry of Materials</i> , 2017, 29, 2874-2882.	6.7	40

#	ARTICLE	IF	CITATIONS
37	Topology Conversions of Non-Interpenetrated Metal-Organic Frameworks to Doubly Interpenetrated Metal-Organic Frameworks. <i>Chemistry of Materials</i> , 2017, 29, 3899-3907.	6.7	17
38	Mix-and-Match Assembly of Block Copolymer Blends in Solution. <i>Macromolecules</i> , 2017, 50, 3234-3243.	4.8	39
39	Direct conversion of coordination compounds into Ni <sub>2</sub> P nanoparticles entrapped in 3D mesoporous graphene for an efficient hydrogen evolution reaction. <i>Materials Chemistry Frontiers</i> , 2017, 1, 973-978.	5.9	41
40	Transformation of Metal-Organic Frameworks/Coordination Polymers into Functional Nanostructured Materials: Experimental Approaches Based on Mechanistic Insights. <i>Accounts of Chemical Research</i> , 2017, 50, 2684-2692.	15.6	184
41	Exploiting Diffusion Barrier and Chemical Affinity of Metal-Organic Frameworks for Efficient Hydrogen Isotope Separation. <i>Journal of the American Chemical Society</i> , 2017, 139, 15135-15141.	13.7	125
42	Selective Hydrogen Isotope Separation via Breathing Transition in MIL-53(Al). <i>Journal of the American Chemical Society</i> , 2017, 139, 17743-17746.	13.7	111
43	Zn-MOFs containing flexible $\alpha$ -alkane (or alkene)-dicarboxylates with 1,2-bis(4-pyridyl)ethylene: comparison with Zn-MOFs containing 1,2-bis(4-pyridyl)ethane ligands. <i>CrystEngComm</i> , 2017, 19, 99-109.	2.6	28
44	Crystal-Size Effects on Carbon Dioxide Capture of a Covalently Alkylamine-Tethered Metal-Organic Framework Constructed by a One-Step Self-Assembly. <i>Scientific Reports</i> , 2016, 6, 19337.	3.3	21
45	Upcycling of nonporous coordination polymers: controllable-conversion toward porosity-tuned N-doped carbons and their electrocatalytic activity in seawater batteries. <i>Journal of Materials Chemistry A</i> , 2016, 4, 13468-13475.	10.3	29
46	General Recyclable Redox-Metallothermic Reaction Route to Hierarchically Porous Carbon/Metal Composites. <i>Chemistry of Materials</i> , 2016, 28, 4403-4408.	6.7	25
47	Effects of porous carbon additives on the CO <sub>2</sub> absorption performance of lithium orthosilicate. <i>Thermochimica Acta</i> , 2016, 637, 31-37.	2.7	20
48	Exploration of Gate-Opening and Breathing Phenomena in a Tailored Flexible Metal-Organic Framework. <i>Inorganic Chemistry</i> , 2016, 55, 1920-1925.	4.0	81
49	Simple coordination complex-derived three-dimensional mesoporous graphene as an efficient bifunctional oxygen electrocatalyst. <i>Chemical Communications</i> , 2015, 51, 6773-6776.	4.1	48
50	Solvent-induced single-crystal to single-crystal transformation of a Zn <sub>4</sub> O-containing doubly interpenetrated metal-organic framework with a pcu net. <i>CrystEngComm</i> , 2015, 17, 8807-8811.	2.6	20
51	Thermal conversion of a tailored metal-organic framework into lithium silicate with an unusual morphology for efficient CO <sub>2</sub> capture. <i>Dalton Transactions</i> , 2015, 44, 15130-15134.	3.3	38
52	4,4'-Biphenyldicarboxylate sodium coordination compounds as anodes for Na-ion batteries. <i>Journal of Materials Chemistry A</i> , 2014, 2, 14986-14993.	10.3	88
53	Multi-core MgO NPs@C core-shell nanospheres for selective CO <sub>2</sub> capture under mild conditions. <i>New Journal of Chemistry</i> , 2014, 38, 1606-1610.	2.8	20
54	Preparation of Co <sub>3</sub> O <sub>4</sub> electrode materials with different microstructures via pseudomorphic conversion of Co-based metal-organic frameworks. <i>Journal of Materials Chemistry A</i> , 2014, 2, 14393-14400.	10.3	62

#	ARTICLE	IF	CITATIONS
55	A transformative route to nanoporous manganese oxides of controlled oxidation states with identical textural properties. <i>Journal of Materials Chemistry A</i> , 2014, 2, 10435-10443.	10.3	93
56	Microfluidic Approach toward Continuous and Ultrafast Synthesis of Metal-Organic Framework Crystals and Hetero Structures in Confined Microdroplets. <i>Journal of the American Chemical Society</i> , 2013, 135, 14619-14626.	13.7	294
57	Effect of sulphur vacancy on geometric and electronic structure of MoS <sub>2</sub> induced by molecular hydrogen treatment at room temperature. <i>RSC Advances</i> , 2013, 3, 18424.	3.6	47
58	Metal-organic frameworks constructed from flexible ditopic ligands: conformational diversity of an aliphatic ligand. <i>New Journal of Chemistry</i> , 2013, 37, 4130.	2.8	22
59	Luminescent Li-Based Metal-Organic Framework Tailored for the Selective Detection of Explosive Nitroaromatic Compounds: Direct Observation of Interaction Sites. <i>Inorganic Chemistry</i> , 2013, 52, 589-595.	4.0	200
60	Fabrication of metal nanoparticles in metal-organic frameworks. <i>Chemical Society Reviews</i> , 2013, 42, 1807-1824.	38.1	596
61	Guest-driven structural flexibility of 2D coordination polymers: Synthesis, structural characterizations, and gas sorption properties. <i>Inorganic Chemistry Communication</i> , 2013, 33, 52-56.	3.9	10
62	Nanoporous Metal Oxides with Tunable and Nanocrystalline Frameworks via Conversion of Metal-Organic Frameworks. <i>Journal of the American Chemical Society</i> , 2013, 135, 8940-8946.	13.7	243
63	Three-dimensional pillared metallomacrocyclic-graphene frameworks with tunable micro- and mesoporosity. <i>Journal of Materials Chemistry A</i> , 2013, 1, 8432.	10.3	32
64	Investigation on the existence of optimum interlayer distance for H <sub>2</sub> uptake using pillared-graphene oxide. <i>International Journal of Hydrogen Energy</i> , 2012, 37, 14217-14222.	7.1	32
65	Post-Synthetic Modifications of Framework Metal Ions in Isostructural Metal-Organic Frameworks: Core-Shell Heterostructures via Selective Transmetalations. <i>Chemistry of Materials</i> , 2012, 24, 3065-3073.	6.7	192
66	Air-stable magnesium nanocomposites provide rapid and high-capacity hydrogen storage without using heavy-metal catalysts. <i>Nature Materials</i> , 2011, 10, 286-290.	27.5	600
67	Flexible and Redox-Active Coordination Polymer: Control of the Network Structure by Pendant Arms of a Macrocyclic Complex. <i>European Journal of Inorganic Chemistry</i> , 2010, 2010, 3795-3803.	2.0	28
68	Size-Controlled Synthesis and Optical Properties of Monodisperse Colloidal Magnesium Oxide Nanocrystals. <i>Angewandte Chemie - International Edition</i> , 2009, 48, 6278-6281.	13.8	54
69	A Stair-Shaped Molecular Silver(0) Chain. <i>Angewandte Chemie - International Edition</i> , 2008, 47, 8390-8393.	13.8	14
70	A Redox-Active Two-Dimensional Coordination Polymer: Preparation of Silver and Gold Nanoparticles and Crystal Dynamics on Guest Removal. <i>Journal of the American Chemical Society</i> , 2006, 128, 4710-4718.	13.7	254
71	Coordination Polymer Open Frameworks Constructed of Macrocyclic Complexes. <i>Advances in Inorganic Chemistry</i> , 2006, , 39-79.	1.0	33
72	Porous Metal-Organic Framework with Coordinatively Unsaturated MnII Sites: Sorption Properties for Various Gases. <i>Inorganic Chemistry</i> , 2006, 45, 8672-8676.	4.0	147

#	ARTICLE	IF	CITATIONS
73	Redox-Active Porous Metal-Organic Framework Producing Silver Nanoparticles from AgI Ions at Room Temperature. <i>Angewandte Chemie - International Edition</i> , 2005, 44, 1261-1265.	13.8	272
74	Self-assembly of hybrid solids consisting of 2D supramolecular networks and intercalated metal complexes. <i>Comptes Rendus Chimie</i> , 2005, 8, 1543-1551.	0.5	8