

Raphael Pilo

List of Publications by Citations

Source: <https://exaly.com/author-pdf/6396872/raphael-pilo-publications-by-citations.pdf>

Version: 2024-04-25

This document has been generated based on the publications and citations recorded by exaly.com. For the latest version of this publication list, visit the link given above.

The third column is the impact factor (IF) of the journal, and the fourth column is the number of citations of the article.

65
papers

1,350
citations

21
h-index

35
g-index

70
ext. papers

1,539
ext. citations

3.9
avg, IF

4.18
L-index

#	Paper	IF	Citations
65	Effect of combinations of surface treatments and bonding agents on the bond strength of repaired composites. <i>Journal of Prosthetic Dentistry</i> , 1997 , 77, 122-6	4	154
64	Effect of post design on resistance to fracture of endodontically treated teeth with complete crowns. <i>Journal of Prosthetic Dentistry</i> , 1993 , 69, 36-40	4	133
63	Post-irradiation polymerization of different anterior and posterior visible light-activated resin composites. <i>Dental Materials</i> , 1992 , 8, 299-304	5.7	128
62	The influence of abutment angulation on strains and stresses along the implant/bone interface: comparison between two experimental techniques. <i>Journal of Prosthetic Dentistry</i> , 1998 , 79, 328-34	4	58
61	Residual dentin thickness in mandibular premolars prepared with hand and rotatory instruments. <i>Journal of Endodontics</i> , 1998 , 24, 401-4	4.7	56
60	Effect of core stiffness on the in vitro fracture of crowned, endodontically treated teeth. <i>Journal of Prosthetic Dentistry</i> , 2002 , 88, 302-6	4	50
59	Comparison of microleakage for three one-bottle and three multiple-step dentin bonding agents. <i>Journal of Prosthetic Dentistry</i> , 1999 , 82, 209-13	4	43
58	The effect of porcelain color on the hardness of luting composite resin cement. <i>Journal of Prosthetic Dentistry</i> , 1993 , 69, 620-3	4	39
57	Interaction of zirconia primers with yttria-stabilized zirconia surfaces. <i>Dental Materials</i> , 2016 , 32, 353-62	5.7	33
56	Anti-biofilm properties of wound dressing incorporating nonrelease polycationic antimicrobials. <i>Biomaterials</i> , 2015 , 46, 141-8	15.6	33
55	Residual dentin thickness in bifurcated maxillary first premolars after root canal and post space preparation with parallel-sided drills. <i>Journal of Prosthetic Dentistry</i> , 2008 , 99, 267-73	4	32
54	Residual dentin thickness in mesial roots of mandibular molars prepared with Lightspeed rotary instruments and Gates-Glidden reamers. <i>Oral Surgery Oral Medicine Oral Pathology Oral Radiology and Endodontics</i> , 2003 , 96, 351-5		31
53	Residual dentin thickness in mandibular premolars prepared with Gates Glidden and ParaPost drills. <i>Journal of Prosthetic Dentistry</i> , 2000 , 83, 617-623	4	31
52	The cantilever fixed partial denture--a literature review. <i>Journal of Prosthetic Dentistry</i> , 1992 , 67, 484-7	4	30
51	Incomplete seating of cemented crowns: a literature review. <i>Journal of Prosthetic Dentistry</i> , 1988 , 59, 429-33	4	30
50	Residual dentin thickness in mandibular premolars prepared with Gates Glidden and ParaPost drills. <i>Journal of Prosthetic Dentistry</i> , 2000 , 83, 0617-0623	4	28
49	In vivo retrospective study of cement thickness under crowns. <i>Journal of Prosthetic Dentistry</i> , 1998 , 79, 621-5	4	27

48	Effect of glaze thickness on the fracture toughness and hardness of alumina-reinforced porcelain. <i>Journal of Prosthetic Dentistry</i> , 1999 , 81, 515-9	4	27
47	Enhanced Nanoassembly-Incorporated Antibacterial Composite Materials. <i>ACS Applied Materials & Interfaces</i> , 2019 , 11, 21334-21342	9.5	26
46	Effect of tribochemical treatments and silane reactivity on resin bonding to zirconia. <i>Dental Materials</i> , 2018 , 34, 306-316	5.7	25
45	Restoring teeth following crown lengthening procedures. <i>Journal of Prosthetic Dentistry</i> , 1991 , 65, 62-4	4	23
44	Time-related PDL: viscoelastic response during initial orthodontic tooth movement of a tooth with functioning interproximal contact-a mathematical model. <i>Journal of Biomechanics</i> , 2008 , 41, 1871-7	2.9	20
43	The effect of one-step vs. two-step impression techniques on long-term accuracy and dimensional stability when the finish line is within the gingival sulcular area. <i>Journal of Prosthodontics</i> , 2014 , 23, 124-33	3.9	17
42	Antibacterial Activity of Dental Cements Containing Quaternary Ammonium Polyethylenimine Nanoparticles. <i>Journal of Nanomaterials</i> , 2012 , 2012, 1-6	3.2	17
41	Effect of irradiation time on tensile properties of stiffness and strength of composites. <i>Journal of Prosthetic Dentistry</i> , 1997 , 77, 471-4	4	15
40	Predicting the clinical performance of dental students with a manual dexterity test. <i>PLoS ONE</i> , 2018 , 13, e0193980	3.7	14
39	Effect of various putty-wash impression techniques on marginal fit of cast crowns. <i>International Journal of Periodontics and Restorative Dentistry</i> , 2013 , 33, e37-42	2.1	13
38	Appropriateness of viscoelastic soft materials as in vitro simulators of the periodontal ligament. <i>Journal of Oral Rehabilitation</i> , 2011 , 38, 929-39	3.4	12
37	The efficacy of liquid and gel acid etchants. <i>Journal of Prosthetic Dentistry</i> , 1988 , 60, 545-7	4	12
36	Setting characteristics and mechanical properties of self-adhesive resin luting agents. <i>Dental Materials</i> , 2017 , 33, 344-357	5.7	11
35	Retention, marginal leakage, and cement solubility of provisional crowns cemented with temporary cement containing stannous fluoride. <i>International Journal of Prosthodontics</i> , 2003 , 16, 189-93	1.9	11
34	Can cone beam CT predict the hardness of interradicular cortical bone?. <i>Head & Face Medicine</i> , 2014 , 10, 12	2.4	10
33	Surface roughness of tooth shoulder preparations created by rotary instrumentation, hand planing, and ultrasonic oscillation. <i>Journal of Prosthetic Dentistry</i> , 1996 , 75, 4-8	4	10
32	Cuspal flexure associated with amalgam restorations. <i>Journal of Prosthetic Dentistry</i> , 1990 , 63, 258-62	4	10
31	A controlled putty-wash impression technique. <i>Journal of Prosthetic Dentistry</i> , 1990 , 64, 635-6	4	10

30	Residual dentin thickness in mandibular premolars prepared with gates glidden and ParaPost drills. <i>Journal of Prosthetic Dentistry</i> , 2000 , 83, 617-23	4	10
29	Retention and marginal leakage of provisional crowns cemented with provisional cements enriched with chlorhexidine diacetate. <i>Journal of Prosthetic Dentistry</i> , 2007 , 98, 373-8	4	9
28	A new muffle model system to study root canal morphology and instrumentation techniques. <i>Journal of Endodontics</i> , 1998 , 24, 540-2	4.7	8
27	The influence of dentin and/or metal surface treatment on the retention of cemented crowns in teeth with an increased taper. <i>Dental Materials</i> , 2008 , 24, 1058-64	5.7	8
26	Circumferential root strains generated during lateral compaction with stainless steel vs. nickel-titanium finger spreaders. <i>European Journal of Oral Sciences</i> , 2018 , 126, 518-525	2.3	8
25	Consolidation of complex motor skill learning: evidence for a delayed offline process. <i>Sleep</i> , 2018 , 41,	1.1	8
24	An interventional study for improving the manual dexterity of dentistry students. <i>PLoS ONE</i> , 2019 , 14, e0211639	3.7	7
23	Influence of periodontal ligament simulation and splints on strains developing at the cervical area of a tooth crown. <i>European Journal of Oral Sciences</i> , 2012 , 120, 466-71	2.3	7
22	Effect of root morphology on the susceptibility of endodontically treated teeth to vertical root fracture: An ex-vivo model. <i>Journal of the Mechanical Behavior of Biomedical Materials</i> , 2017 , 69, 267-274	4.1	6
21	Dimensional stability of polyvinyl siloxane impression material reproducing the sulcular area. <i>Dental Materials Journal</i> , 2013 , 32, 25-31	2.5	6
20	The effect of irradiation time on the shear strength of composites. <i>Dental Materials</i> , 1994 , 10, 338-42	5.7	6
19	Long-term durability of adhesive systems bonded to fresh amalgam. <i>Journal of Prosthetic Dentistry</i> , 1996 , 76, 431-6	4	5
18	The Retentive Strength of Cemented Zirconium Oxide Crowns after Dentin Pretreatment with Desensitizing Paste Containing 8% Arginine and Calcium Carbonate. <i>International Journal of Molecular Sciences</i> , 2016 , 17, 426	6.3	5
17	The effect of resin coating on the shear punch strength of restorative glass ionomer cements. <i>Clinical Oral Investigations</i> , 2017 , 21, 1079-1086	4.2	4
16	Shear modulus--measurement methodology with application to light-cured resin composites. <i>Dental Materials</i> , 1996 , 12, 52-7	5.7	4
15	Tensile mechanical properties of swine cortical mandibular bone. <i>PLoS ONE</i> , 2014 , 9, e113229	3.7	4
14	Novel silane encapsulation system for tribochemical resin bonding to a Co-Cr alloy. <i>Journal of Dentistry</i> , 2016 , 50, 60-8	4.8	3
13	Effect of Silane Reaction Time on the Repair of a Nanofilled Composite Using Tribochemical Treatment. <i>Journal of Adhesive Dentistry</i> , 2016 , 18, 125-34	3	3

12	Does Augmented Visual Feedback from Novel, Multicolored, Three-Dimensional-Printed Teeth Affect Dental Students' Acquisition of Manual Skills?. <i>Anatomical Sciences Education</i> , 2021 , 14, 629-640	6.8	3
11	Strain Distribution in Root Surface Dentin of Maxillary Central Incisors during Lateral Compaction. <i>PLoS ONE</i> , 2016 , 11, e0156461	3.7	3
10	The influence of long term water immersion on shear bond strength of amalgam repaired by resin composite and mediated by adhesives or resin modified glass ionomers. <i>Journal of Dentistry</i> , 2012 , 40, 594-602	4.8	2
9	Abutment positioning in a cantilevered shortened dental arch: a clinical report and static analysis. <i>Journal of Prosthetic Dentistry</i> , 2003 , 89, 227-31	4	2
8	Reliability of ratings in evaluation of crowns. <i>Journal of Prosthetic Dentistry</i> , 1987 , 58, 647-9	4	2
7	Aspirin inhibits Ca ²⁺ -stimulated fatty acid release from human washed platelets. <i>Prostaglandins, Leukotrienes and Essential Fatty Acids</i> , 1981 , 6, 657-60		2
6	Load-Bearing Capacity of Zirconia Crowns Screwed to Multi-Unit Abutments with and without a Titanium Base: An In Vitro Pilot Study. <i>Materials</i> , 2019 , 12,	3.5	1
5	The Retentive Strength of Zirconium Oxide Crowns Cemented by Self-Adhesive Resin Cements before and after 6 Months of Aging. <i>Materials</i> , 2020 , 13,	3.5	1
4	The Retentive Strength of Laser-Sintered Cobalt-Chromium-Based Crowns after Pretreatment with a Desensitizing Paste Containing 8% Arginine and Calcium Carbonate. <i>International Journal of Molecular Sciences</i> , 2018 , 19,	6.3	1
3	New Training Approach for Improving the Spatial Perception and Orientation Ability of Dentistry Students. <i>Applied Sciences (Switzerland)</i> , 2021 , 11, 9387	2.6	0
2	3D-Printed Teeth with Multicolored Layers as a Tool for Evaluating Cavity Preparation by Dental Students. <i>Applied Sciences (Switzerland)</i> , 2021 , 11, 6406	2.6	0
1	Diagnostic casts--an additional dimension. <i>Journal of Prosthetic Dentistry</i> , 1989 , 61, 248-9	4	