

# Kun Wang

## List of Publications by Year in descending order

Source: <https://exaly.com/author-pdf/6941193/publications.pdf>

Version: 2024-02-01

11  
papers

221  
citations

1307594  
7  
h-index

1281871  
11  
g-index

11  
all docs

11  
docs citations

11  
times ranked

336  
citing authors

#	ARTICLE	IF	CITATIONS
1	Computational insights into the formation driving force of CL-20 based solvates and their desolvation process. <i>CrystEngComm</i> , 2021, 23, 2150-2161.	2.6	7
2	Structure, intermolecular interactions, and dynamic properties of NTO crystals with impurity defects: a computational study. <i>CrystEngComm</i> , 2021, 23, 2455-2468.	2.6	14
3	Computational insight into energetic cage derivatives based on hexahydro-1,3,5-trinitro-1,3,5-triazine. <i>Journal of the Chinese Chemical Society</i> , 2020, 67, 961-968.	1.4	1
4	Insight into the roles of small molecules in CL-20 based host-guest crystals: a comparative DFT-D study. <i>CrystEngComm</i> , 2020, 22, 6228-6238.	2.6	11
5	Application of Molecular Electrostatic Potential Surface to Predict Supramolecular Synthons for RDX/Solvent Cocrystals. <i>Crystal Research and Technology</i> , 2019, 54, 1900171.	1.3	6
6	Construction of lubricant composite coating on Ti6Al4V alloy using micro-arc oxidation and grafting hydrophilic polymer. <i>Materials Science and Engineering C</i> , 2018, 90, 219-226.	7.3	24
7	Improved biotribological properties of PEEK by photo-induced graft polymerization of acrylic acid. <i>Materials Science and Engineering C</i> , 2017, 75, 777-783.	7.3	51
8	Semi-degradable porous poly (vinyl alcohol) hydrogel scaffold for cartilage repair: Evaluation of the initial and cell-cultured tribological properties. <i>Journal of the Mechanical Behavior of Biomedical Materials</i> , 2017, 68, 163-172.	3.1	29
9	Robust superhydrophobic coating and the anti-icing properties of its lubricants-infused-composite surface under condensing condition. <i>New Journal of Chemistry</i> , 2017, 41, 1846-1853.	2.8	57
10	The mechanical properties of the ultra high molecular weight polyethylene grafted with 3-dimethyl (3-(N-methacrylamido) propyl) ammonium propane sulfonate. <i>Journal of the Mechanical Behavior of Biomedical Materials</i> , 2014, 35, 18-26.	3.1	6
11	Novel lubricated surface of titanium alloy based on porous structure and hydrophilic polymer brushes. <i>Applied Surface Science</i> , 2014, 317, 875-883.	6.1	15