Robert Chulist

List of Publications by Year in descending order

Source: https://exaly.com/author-pdf/804413/publications.pdf

Version: 2024-02-01

113 papers 2,002 citations

236833 25 h-index 330025 37 g-index

114 all docs

114 docs citations

times ranked

114

1099 citing authors

#	Article	IF	Citations
1	Structural properties of Ti/Al clads manufactured by explosive welding and annealing. Materials and Design, 2016, 91, 80-89.	3.3	158
2	Over 7% magnetic field-induced strain in a Ni-Mn-Ga five-layered martensite. Applied Physics Letters, 2014, 105, .	1.5	82
3	Microstructure and kinetics of intermetallic phase growth of three-layered A1050/AZ31/A1050 clads prepared by explosive welding combined with subsequent annealing. Materials and Design, 2017, 130, 120-130.	3.3	65
4	Characterization of mobile type I and type II twin boundaries in 10M modulated Ni–Mn–Ga martensite by electron backscatter diffraction. Acta Materialia, 2013, 61, 1913-1920.	3.8	64
5	Microstructure and phase constitution in the bonding zone of explosively welded tantalum and stainless steel sheets. Materials and Design, 2018, 153, 177-189.	3.3	57
6	Large magnetic field-induced work output in a NiMnGa seven-layered modulated martensite. Applied Physics Letters, 2015, 107, .	1.5	49
7	Change in microstructure during training of a Ni50Mn29Ga21 bicrystal. Scripta Materialia, 2010, 63, 548-551.	2.6	48
8	Controlled Grain Refinement of Biodegradable Zn-Mg Alloy: The Effect of Magnesium Alloying and Multi-Pass Hydrostatic Extrusion Preceded by Hot Extrusion. Metallurgical and Materials Transactions A: Physical Metallurgy and Materials Science, 2020, 51, 6784-6796.	1.1	45
9	High-temperature magnetic shape memory actuation in a Ni–Mn–Ga single crystal. Scripta Materialia, 2014, 83, 29-32.	2.6	43
10	Microstructure Changes and Phase Growth Occurring at the Interface of the Al/Ti Explosively Welded and Annealed Joints. Journal of Materials Engineering and Performance, 2016, 25, 3211-3217.	1.2	43
11	Growth kinetics of TiAl 3 phase in annealed Al/Ti/Al explosively welded clads. Materials Letters, 2017, 198, 160-163.	1.3	40
12	The effect of severe plastic deformation on the Mg properties after CEC deformation. Journal of Magnesium and Alloys, 2020, 8, 761-768.	5.5	39
13	Detwinning of a non-modulated Ni–Mn–Ga martensite: From self-accommodated microstructure to single crystal. Acta Materialia, 2015, 85, 67-73.	3.8	37
14	2019, 171, 107703.	3.3	37
15	Martensitic transition, structure and magnetic anisotropy ofÂmartensite in Ni-Mn-Sn single crystal. Acta Materialia, 2016, 118, 213-220.	3.8	35
16	The Effect of Interface Morphology on the Electro-Mechanical Properties of Ti/Cu Clad Composites Produced by Explosive Welding. Metallurgical and Materials Transactions A: Physical Metallurgy and Materials Science, 2020, 51, 750-766.	1.1	34
17	Texture transformations near the bonding zones of the three-layer Al/Ti/Al explosively welded clads. Materials Characterization, 2017, 129, 242-246.	1.9	33
18	Interfacial reactions and microstructure related properties of explosively welded tantalum and steel sheets with copper interlayer. Materials and Design, 2021, 208, 109873.	3.3	31

#	Article	IF	CITATIONS
19	Microstructure and texture in Ni50Mn29Ga21 deformed by high-pressure torsion. Scripta Materialia, 2010, 62, 650-653.	2.6	30
20	On the role of atomic shuffling in the 4O, 4M and 8M martensite structures in Ni-Mn-Sn single crystal. Scripta Materialia, 2020, 189, 106-111.	2.6	30
21	Microstructure-strength relationship of ultrafine-grained titanium manufactured by unconventional severe plastic deformation process. Journal of Alloys and Compounds, 2020, 837, 155576.	2.8	30
22	Orientation relationship between austenite and non-modulated martensite in Ni–Mn–Ga single crystals. Acta Materialia, 2016, 103, 836-843.	3.8	29
23	Effect of impact loading and heat treatment on microstructure and properties of multi-layered AZ31/AA1050 plates fabricated by single-shot explosive welding. Materials and Design, 2022, 214, 110411.	3.3	28
24	Modulation reorientation in 10M Ni–Mn–Ga martensite. Scripta Materialia, 2013, 68, 671-674.	2.6	26
25	Diffraction study of bending-induced polysynthetic twins in 10M modulated Ni-Mn-Ga martensite. Journal of Applied Physics, 2012, 112, .	1.1	25
26	Microstructure and properties of the interfacial region in explosively welded and post-annealed titanium-copper sheets. Materials Characterization, 2020, 167, 110520.	1.9	25
27	Towards a better understanding of the phase transformations in explosively welded copper to titanium sheets. Materials Science & Engineering A: Structural Materials: Properties, Microstructure and Processing, 2020, 784, 139285.	2.6	25
28	High pressure torsion of Cu–Ag and Cu–Sn alloys: Limits for solubility and dissolution. Acta Materialia, 2020, 195, 184-198.	3.8	24
29	Cyclic fibre texture in hot extruded Ni ₅₀ Mn ₂₉ Ga ₂₁ . International Journal of Materials Research, 2012, 103, 575-579.	0.1	23
30	Structural modification and twinning stress reduction in a high-temperature Ni-Mn-Ga magnetic shape memory alloy. Applied Physics Letters, 2013, 103, .	1.5	23
31	Magnetostructural transition and magnetocaloric effect in highly textured Ni-Mn-Sn alloy. Journal of Applied Physics, 2016, 119 , .	1.1	22
32	Structural and Mechanical Properties of Ti–Co Alloys Treated by High Pressure Torsion. Materials, 2019, 12, 426.	1.3	22
33	Microstructural and Phase Composition Differences Across the Interfaces in Al/Ti/Al Explosively Welded Clads. Metallurgical and Materials Transactions A: Physical Metallurgy and Materials Science, 2017, 48, 4154-4165.	1.1	21
34	Twin boundaries in trained 10M Niâ^'Mnâ^'Ga single crystals. Scripta Materialia, 2012, 67, 364-367.	2.6	20
35	Grain refinement of intermetallic compounds in the Cu–Sn system under high pressure torsion. Materials Letters, 2016, 179, 12-15.	1.3	20
36	Microstructural characterization and mechanical properties of in situ cast nanocomposites Al/TiC type. Journal of Materials Research and Technology, 2020, 9, 12707-12715.	2.6	20

#	Article	IF	CITATIONS
37	Processing Routes Toward Textured Polycrystals in Ferromagnetic Shape Memory Alloys. Advanced Engineering Materials, 2012, 14, 636-652.	1.6	19
38	Hierarchical twin microstructure in modulated 10M Ni–Mn-Ga single crystals. An analysis including shuffling of atomic layers. International Journal of Plasticity, 2020, 126, 102628.	4.1	19
39	Sn and Nb modified ultrafine Ti-based bulk alloys with high-strength and enhanced ductility. Applied Physics Letters, 2013, 102, .	1.5	18
40	Phase transformations in a Cu Cr alloy induced by high pressure torsion. Materials Characterization, 2016, 114, 151-156.	1.9	18
41	Highly mobile twin boundaries in seven-layer modulated Ni–Mn–Ga–Fe martensite. Scripta Materialia, 2020, 178, 62-66.	2.6	18
42	Evolution of microstructure and crystallographic texture of Ni-Mn-Ga melt-spun ribbons exhibiting 1.15% magnetic field-induced strain. Acta Materialia, 2021, 219, 117237.	3.8	18
43	An in situ and ex situ study of χ phase formation in a hypoeutectic Fe-based hardfacing alloy. Materials and Design, 2020, 188, 108438.	3.3	17
44	Self-accommodated and pre-strained martensitic microstructure in single-crystalline, metamagnetic Ni–Mn–Sn Heusler alloy. Journal of Materials Science, 2017, 52, 5600-5610.	1.7	16
45	Twin-induced stability and mechanical properties of pure magnesium. Materials Science & Science & Engineering A: Structural Materials: Properties, Microstructure and Processing, 2019, 749, 89-95.	2.6	15
46	Dissolution of Ag Precipitates in the Cu–8wt.%Ag Alloy Deformed by High Pressure Torsion. Materials, 2019, 12, 447.	1.3	15
47	Branched needle microstructure in Ni-Mn-Ga 10M martensite: EBSD study. Acta Materialia, 2017, 128, 113-119.	3.8	14
48	Superelastic behavior of a metamagnetic Ni–Mn–Sn single crystal. Journal of Materials Science, 2018, 53, 10383-10395.	1.7	14
49	Wetting of Sn-Zn-Ga and Sn-Zn-Na Alloys on Al and Ni Substrate. Journal of Electronic Materials, 2018, 47, 49-60.	1.0	14
50	Orthogonal shear process in Ni-Mn-Sn single crystal. International Journal of Plasticity, 2019, 114, 63-71.	4.1	14
51	Structural Properties of Interfacial Layers in Tantalum to Stainless Steel Clad with Copper Interlayer Produced by Explosive Welding. Metals, 2020, 10, 969.	1.0	14
52	Information on deformation mechanisms in nanocrystalline Pd–10% Au inferred from texture analysis. Journal of Materials Science, 2010, 45, 4571-4577.	1.7	13
53	Texture development in a nanocrystalline Pd–Au alloy studied by synchrotron radiation. Scripta Materialia, 2012, 66, 131-134.	2.6	13
54	Martensite stabilisation in single crystalline Ni-Mn-Ga and Ni-Mn-Sn magnetic shape memory alloys. Materials Letters, 2018, 230, 266-269.	1.3	13

#	Article	IF	CITATIONS
55	Influence of Dynamic Recrystallisation on Texture Formation in ECAP deformed Nickel. Materials Science Forum, 2007, 558-559, 575-580.	0.3	12
56	Effect of initial plastic strain on mechanical training of non-modulated Ni–Mn–Ga martensite structure. Materials Science & Engineering A: Structural Materials: Properties, Microstructure and Processing, 2014, 611, 313-319.	2.6	12
57	Residual stresses distribution, correlated with bending tests, within explosively welded Ti gr. 2/A1050 bimetals. Materials Characterization, 2018, 144, 461-468.	1.9	12
58	The effect of heat treatment on the precipitation hardening in FeNiCoAlTa single crystals. Materials Science & Science & Properties, Microstructure and Processing, 2020, 784, 139327.	2.6	12
59	Texture Heterogeneity in ECAP Deformed Copper. Solid State Phenomena, 0, 160, 47-54.	0.3	11
60	Structural behavior and magnetic properties of a Ni–Mn–Ga single crystal across the martensite/austenite two-phase region. Acta Materialia, 2015, 89, 32-40.	3.8	11
61	Non-conventional twins in five-layer modulated Ni-Mn-Ga martensite. Scripta Materialia, 2019, 162, 497-502.	2.6	11
62	Twinning Behaviour of Textured Polycrystalline Ni-Mn-Ga Alloy after Hot Extrusion. Materials Science Forum, 0, 635, 195-199.	0.3	10
63	Self-accommodation in polycrystalline 10M Ni–Mn–Ga martensite. Journal of Materials Science, 2014, 49, 3951-3955.	1.7	10
64	The $\hat{l}\pm\hat{a}\dagger$ "i‰ phase transformations and thermal stability of Ti Co alloy treated by high pressure torsion. Materials Characterization, 2021, 173, 110937.	1.9	10
65	Microstructure and Magnetic Properties of Selected Laser Melted Ni-Mn-Ga and Ni-Mn-Ga-Fe Powders Derived from as Melt-Spun Ribbons Precursors. Metals, 2021, 11, 903.	1.0	10
66	Phase Transformation in 316L Austenitic Steel Induced by Fracture at Cryogenic Temperatures: Experiment and Modelling. Materials, 2021, 14, 127.	1.3	10
67	New Insights into the Intermartensitic Transformation and Over 11% Magnetic Fieldâ€Induced Strain in 14 <scp>m</scp> Niâ^'Mnâ^'Ga Martensite. Advanced Engineering Materials, 2021, 23, 2100131.	1.6	9
68	The Effect of a Multiphase Microstructure on the Inverse Magnetocaloric Effect in Ni–Mn–Cr–Sn Metamagnetic Heusler Alloys. Magnetochemistry, 2017, 3, 24.	1.0	8
69	The intermetallics growth at the interface of explosively welded A1050/Ti gr. 2/A1050 clads in relation to the explosive material. Archives of Civil and Mechanical Engineering, 2018, 18, 1679-1685.	1.9	8
70	Origins of superparamagnetism in self-accommodated and trained Ni50Mn37.5Sn12.5 single crystal. Journal of Magnetism and Magnetic Materials, 2020, 514, 167190.	1.0	8
71	Microstructure and catalytic activity for selective hydrogenation of phenylacetylene of intermetallic Ni70Ga30, Ni70In30, and Ni70Sn30 melt-spun alloys. Intermetallics, 2020, 122, 106797.	1.8	8
72	Dynamic Recrystallization and Its Effect on Superior Plasticity of Cold-Rolled Bioabsorbable Zinc-Copper Alloys. Materials, 2021, 14, 3483.	1.3	8

#	Article	IF	Citations
73	Direction of modulation during twin boundary motion. Scripta Materialia, 2010, 62, 235-237.	2.6	7
74	Stage B workâ€hardening of magnesium single crystals. Crystal Research and Technology, 2011, 46, 439-442.	0.6	7
75	Asymmetric distribution of martensitic variants in non-modulated NiMnGa single crystals. Journal of Materials Science, 2016, 51, 10943-10948.	1.7	7
76	Synergistic effect of Mg addition and hydrostatic extrusion on microstructure and texture of biodegradable low-alloyed zinc. IOP Conference Series: Materials Science and Engineering, 2018, 375, 012008.	0.3	7
77	Interfacial Phenomena between Liquid Ga-Based Alloys and Ni Substrate. Journal of Electronic Materials, 2019, 48, 5941-5947.	1.0	7
78	Studies on the Two-Step Aging Process of Fe-Based Shape Memory Single Crystals. Materials, 2020, 13, 1724.	1.3	7
79	Thermal stability and microhardness of metastable ï‰-phase in the Ti-3.3Âat.% Co alloy subjected to high pressure torsion. Journal of Alloys and Compounds, 2020, 834, 155132.	2.8	7
80	Omega Phase Formation in Ti–3wt.%Nb Alloy Induced by High-Pressure Torsion. Materials, 2021, 14, 2262.	1.3	6
81	Characterization of rapidly solidified Al-Mg-Sc alloys with Li addition. Materials Characterization, 2021, 178, 111290.	1.9	6
82	Flow softening, twinning and dynamic evolution of second phase particles in a rolled Mg–Y-Nd-Zr alloy under shear deformation mode. Journal of Materials Research and Technology, 2022, 18, 2368-2383.	2.6	6
83	Texture Evolution of HPT-Processed Ni ₅₀ Mn ₂₉ Ga ₂₁ . Materials Science Forum, 0, 702-703, 169-172.	0.3	5
84	Texture and microstructure of HPT-processed Fe-based shape memory alloys. IOP Conference Series: Materials Science and Engineering, 2018, 375, 012006.	0.3	5
85	Effect of B addition on the superelasticity in FeNiCoAlTa single crystals. Materials and Design, 2021, 197, 109225.	3.3	5
86	Texture-Based Optimization of Crystal Plasticity Parameters: Application to Zinc and Its Alloy. Metallurgical and Materials Transactions A: Physical Metallurgy and Materials Science, 2021, 52, 3257-3273.	1.1	5
87	Texture-Governed Cell Response to Severely Deformed Titanium. ACS Biomaterials Science and Engineering, 2021, 7, 114-121.	2.6	5
88	Surface hardening of high- and medium-entropy alloys by mechanical attrition at room and cryogenic temperatures. Applied Physics Letters, 2021, 119, 201912.	1.5	5
89	Deformation twinning in polycrystalline NiMnGa alloys. Journal of Physics: Conference Series, 2010, 240, 012024.	0.3	4
90	Microstructure evolution and magnetic properties in Mn-rich Ni-(Co, Cu, Fe)-Mn-Sn Heusler base shape memory alloys. Materials Chemistry and Physics, 2019, 235, 121720.	2.0	4

#	Article	IF	CITATIONS
91	Microstructural response on nickel addition in rapidly solidified â ¹ ¼Fe-25Cr-xNi-5Mo-0.8C [x = 0, 6, 11, 15, 21 wt. %] hardfacing alloys. Journal of Alloys and Compounds, 2019, 787, 186-195.	2.8	4
92	Effect of heat treatment on the precipitation hardening in FeNiCoAlTaB shape memory alloys. International Journal of Materials Research, 2019, 110, 70-74.	0.1	4
93	Suppression and Recovery of Martensitic Transformation and Magnetism in Mechanically and Thermally Treated Magnetic Shapeâ€Memory Niâ^¹Mnâ^¹Ga Meltâ€Spun Ribbons. Advanced Engineering Materials, 0, , 2100075.	1.6	4
94	Microstructure Development in the Bonding Zone of Explosively Welded Ti and Cu Sheets. Materials Science Forum, 0, 1016, 1114-1120.	0.3	4
95	Titania coating formation on hydrostatically extruded pure titanium by micro-arc oxidation method. Journal of Materials Science and Technology, 2022, 111, 224-235.	5.6	4
96	Crystallographic characterization of catastrophic shear in submicron nickel at low temperatures. Journal of Physics: Conference Series, 2010, 240, 012150.	0.3	3
97	Influence of Additives on Texture Development of Submicro- and Nanocrystalline Nickel. Materials Science Forum, 0, 702-703, 928-931.	0.3	3
98	Influence of deformation temperature on texture evolution in HPT deformed NiAl. IOP Conference Series: Materials Science and Engineering, 2014, 63, 012154.	0.3	3
99	Grain Refinement of AZ61 Alloy after ECAP Processing. Materials Science Forum, 0, 891, 372-376.	0.3	3
100	The Phase Transformations Induced by High-Pressure Torsion in Ti–Nb-Based Alloys. Microscopy and Microanalysis, 2022, 28, 946-952.	0.2	3
101	Temperature dependence of twinning stress in Ni49.5Mn38.4Sn12.2 single crystal. Journal of Applied Physics, 2019, 126, 145107.	1.1	2
102	Interfacial reactions and structural properties of explosively welded titanium/copper plates. IOP Conference Series: Materials Science and Engineering, 2020, 770, 012033.	0.3	2
103	Interfacial Reactions in the Bonding Zones of Explosively Welded Tantalum to Stainless Steel Sheets. Advanced Engineering Materials, 2021, 23, 2001521.	1.6	2
104	Low temperature deformation mechanisms of polycrystalline CoZr and Co39Ni11Zr50 B2-type intermetallic compounds. Acta Materialia, 2022, 223, 117489.	3.8	2
105	Formation and Thermal Stability of the ω-Phase in Ti–Nb and Ti–Mo Alloys Subjected to HPT. Materials, 2022, 15, 4136.	1.3	2
106	Equal-Channel Angular Pressing of NiAl. Materials Science Forum, 2010, 667-669, 39-44.	0.3	1
107	Influence of hydrostatic pressure on texture evolution in HPT deformed NiAl. IOP Conference Series: Materials Science and Engineering, 2015, 82, 012026.	0.3	1
108	Multiphase Microstructure and Extended Martensitic Phase Transformation in Directionally Solidified and Heat Treated Ni44Co6Mn39Sn11 Metamagnetic Shape Memory Alloy. Minerals, Metals and Materials Series, 2018, , 263-267.	0.3	1

ROBERT CHULIST

#	Article	lF	CITATIONS
109	A special single variant zone in directionally solidified Ni-Mn-Ga alloy. Scripta Materialia, 2019, 167, 105-109.	2.6	1
110	Fe-Co-B Soft Magnetic Ribbons: Crystallization Process, Microstructure and Coercivity. Materials, 2020, 13, 1639.	1.3	1
111	TiAl-based semi-finished material produced by reaction annealing of Ti/Al layered composite sheets. Materials Today Communications, 2022, 30, 103083.	0.9	1
112	Gradient microstructure in the bonding zone of explosively welded sheets. Procedia Manufacturing, 2020, 50, 689-695.	1.9	0
113	Suppression of γ phase and its effect on mechanical behavior of melt-spun and annealed Ni–Mn–Ga high-temperature shape memory alloys. Materials Today Communications, 2020, 24, 101165.	0.9	0