

# Yuexiang Lu

## List of Publications by Year in descending order

Source: <https://exaly.com/author-pdf/8500497/publications.pdf>

Version: 2024-02-01

72  
papers

3,352  
citations

117453

34  
h-index

149479

56  
g-index

73  
all docs

73  
docs citations

73  
times ranked

4063  
citing authors

#	ARTICLE	IF	CITATIONS
1	Application of carbon dots and their composite materials for the detection and removal of radioactive ions: A review. <i>Chemosphere</i> , 2022, 287, 132313.	4.2	82
2	Carbon dots and carbon nitride composite for photocatalytic removal of uranium under air atmosphere. <i>Chinese Chemical Letters</i> , 2022, 33, 3573-3576.	4.8	10
3	Metal-enhanced fluorescence of graphene oxide sheets. <i>Analytical and Bioanalytical Chemistry</i> , 2022, 414, 3625-3630.	1.9	3
4	Microplasma electrochemistry (MIPEC) strategy for accelerating the synthesis of metal organic frameworks at room temperature. <i>Chinese Chemical Letters</i> , 2021, 32, 497-500.	4.8	10
5	Sunlight-induced uranium extraction with triazine-based carbon nitride as both photocatalyst and adsorbent. <i>Applied Catalysis B: Environmental</i> , 2021, 282, 119523.	10.8	91
6	Graphene Oxide Membranes for Tunable Ion Sieving in Acidic Radioactive Waste. <i>Advanced Science</i> , 2021, 8, 2002717.	5.6	44
7	Structural design of metal catalysts based on ZIFs: From nanoscale to atomic level. <i>Nano Select</i> , 2021, 2, 1902-1925.	1.9	6
8	An ultra-sensitive colorimetric detection of Ag ions based on etching AuNP@MnO <sub>2</sub> nanoparticles with glutathione by using dark field optical microscopy. <i>Sensors and Actuators B: Chemical</i> , 2021, 330, 129382.	4.0	21
9	Redox Recycling-Activated Signal Amplification of Peroxidase-like Catalytic Activity Based on Bare Gold Nanoparticle-Metal Ion Ensembles as Colorimetric Sensor Array for Ultrasensitive Discrimination of Phosphates. <i>ACS Sustainable Chemistry and Engineering</i> , 2021, 9, 9802-9812.	3.2	20
10	Colorimetric sensor array based on gold nanoparticles: Design principles and recent advances. <i>TrAC - Trends in Analytical Chemistry</i> , 2020, 122, 115754.	5.8	147
11	Iodide-assisted silver nanoplates for colorimetric determination of chromium(III) and copper(II) via an aggregation/fusion/oxidation etching strategy. <i>Mikrochimica Acta</i> , 2020, 187, 19.	2.5	7
12	Graphene aerogel for photocatalysis-assist uranium elimination under visible light and air atmosphere. <i>Chemical Engineering Journal</i> , 2020, 402, 126256.	6.6	52
13	Single-strand DNA-scaffolded copper nanoclusters for the determination of inorganic pyrophosphatase activity and screening of its inhibitor. <i>Mikrochimica Acta</i> , 2020, 187, 672.	2.5	6
14	Graphene aerogel capsulated precipitants for high efficiency and rapid elimination of uranium from water. <i>Chemical Engineering Journal</i> , 2020, 396, 125272.	6.6	54
15	In situ monitoring of catalytic reaction on single nanoporous gold nanowire with tuneable SERS and catalytic activity. <i>Talanta</i> , 2020, 218, 121181.	2.9	7
16	Cyclodextrin functionalized 3D-graphene for the removal of Cr(VI) with the easy and rapid separation strategy. <i>Environmental Pollution</i> , 2019, 254, 112854.	3.7	43
17	Localized Surface Plasmon Resonance Meets Controlled/Living Radical Polymerization: An Adaptable Strategy for Broadband Light-Regulated Macromolecular Synthesis. <i>Angewandte Chemie</i> , 2019, 131, 12224-12229.	1.6	18
18	Localized Surface Plasmon Resonance Meets Controlled/Living Radical Polymerization: An Adaptable Strategy for Broadband Light-Regulated Macromolecular Synthesis. <i>Angewandte Chemie - International Edition</i> , 2019, 58, 12096-12101.	7.2	38

#	ARTICLE	IF	CITATIONS
19	Quantitative Analysis of Surface Sites on Carbon Dots and Their Interaction with Metal Ions by a Potentiometric Titration Method. <i>Analytical Chemistry</i> , 2019, 91, 9690-9697.	3.2	19
20	DNA-templated copper nanoclusters as a fluorescent probe for fluoride by using aluminum ions as a bridge. <i>Mikrochimica Acta</i> , 2019, 186, 364.	2.5	20
21	A colorimetric sensor array for protein discrimination based on carbon nanodots-induced reversible aggregation of AuNP with GSH as a regulator. <i>Sensors and Actuators B: Chemical</i> , 2019, 296, 126677.	4.0	18
22	DNA-scaffold copper nanoclusters integrated into a cerium(III)-triggered Fenton-like reaction for the fluorometric and colorimetric enzymatic determination of glucose. <i>Mikrochimica Acta</i> , 2019, 186, 862.	2.5	8
23	Bare eye detection of Hg(II) ions based on enzyme inhibition and using mercaptoethanol as a reagent to improve selectivity. <i>Mikrochimica Acta</i> , 2018, 185, 174.	2.5	9
24	Polydopamine Induced in-Situ Formation of Metallic Nanoparticles in Confined Microchannels of Porous Membrane as Flexible Catalytic Reactor. <i>ACS Applied Materials &amp; Interfaces</i> , 2018, 10, 14735-14743.	4.0	32
25	Colorimetric Nanosensor Based on the Aggregation of AuNP Triggered by Carbon Quantum Dots for Detection of Ag <sup>+</sup> Ions. <i>ACS Sustainable Chemistry and Engineering</i> , 2018, 6, 3706-3713.	3.2	56
26	Microplasma electrochemistry controlled rapid preparation of fluorescent polydopamine nanoparticles and their application in uranium detection. <i>Chemical Engineering Journal</i> , 2018, 344, 480-486.	6.6	49
27	Microplasma Anode Meeting Molten Salt Electrochemistry: Charge Transfer and Atomic Emission Spectral Analysis. <i>Analytical Chemistry</i> , 2018, 90, 13163-13166.	3.2	6
28	On-off-on luminescent pyrophosphate probe based on the use of Mn-doped ZnS quantum dots and using Eu(III) as a mediator. <i>Mikrochimica Acta</i> , 2018, 185, 480.	2.5	10
29	Dispersion-aggregation-dispersion colorimetric detection for mercury ions based on an assembly of gold nanoparticles and carbon nanodots. <i>Analyst</i> , 2018, 143, 4741-4746.	1.7	30
30	Time-resolved determination of Fe(II) ions using cysteine-bridged Mn-doped ZnS quantum dots as a phosphorimetric probe. <i>Mikrochimica Acta</i> , 2018, 185, 298.	2.5	11
31	Heteroatom-Doped Carbon Dots (CDs) as a Class of Metal-Free Photocatalysts for PET-CRAFT Polymerization under Visible Light and Sunlight. <i>Angewandte Chemie</i> , 2018, 130, 12213-12218.	1.6	33
32	Heteroatom-Doped Carbon Dots (CDs) as a Class of Metal-Free Photocatalysts for PET-CRAFT Polymerization under Visible Light and Sunlight. <i>Angewandte Chemie - International Edition</i> , 2018, 57, 12037-12042.	7.2	121
33	Self-Cascade System Based on Cupric Oxide Nanoparticles as Dual-Functional Enzyme Mimics for Ultrasensitive Detection of Silver Ions. <i>ACS Sustainable Chemistry and Engineering</i> , 2018, 6, 12132-12139.	3.2	40
34	Colorimetric sensor array for proteins discrimination based on the tunable peroxidase-like activity of AuNPs-DNA conjugates. <i>Sensors and Actuators B: Chemical</i> , 2017, 245, 66-73.	4.0	37
35	Pinpoint the Positions of Single Nucleotide Polymorphisms by a Nanocluster Dimer. <i>Analytical Chemistry</i> , 2017, 89, 2622-2627.	3.2	19
36	Visualization of Adsorption: Luminescent Mesoporous Silica-Carbon Dots Composite for Rapid and Selective Removal of U(VI) and in Situ Monitoring the Adsorption Behavior. <i>ACS Applied Materials &amp; Interfaces</i> , 2017, 9, 7392-7398.	4.0	96

#	ARTICLE	IF	CITATIONS
37	Lab-on-nanoparticle as a multidimensional device for colorimetric discrimination of proteins. <i>Mikrochimica Acta</i> , 2017, 184, 3265-3271.	2.5	2
38	Acquiring multiple signals along with the reaction time: improving recognition capability of a multidimensional colorimetric sensor array for sensitive protein detection. <i>Analyst, The</i> , 2017, 142, 2663-2669.	1.7	9
39	Metal-Free Photoinduced Electron Transfer-Atom Transfer Radical Polymerization Integrated with Bioinspired Polydopamine Chemistry as a Green Strategy for Surface Engineering of Magnetic Nanoparticles. <i>ACS Applied Materials &amp; Interfaces</i> , 2017, 9, 13637-13646.	4.0	52
40	Performance and Mechanism of Uranium Adsorption from Seawater to Poly(dopamine)-Inspired Sorbents. <i>Environmental Science &amp; Technology</i> , 2017, 51, 4606-4614.	4.6	168
41	Continuously evolving "chemical tongue" biosensor for detecting proteins. <i>Talanta</i> , 2017, 165, 182-187.	2.9	13
42	Nano Endoscopy with Plasmon-Enhanced Fluorescence for Sensitive Sensing Inside Ultrasmall Volume Samples. <i>Analytical Chemistry</i> , 2017, 89, 1045-1048.	3.2	9
43	Controlled Architecture of Glass Fiber/Poly(glycidyl methacrylate) Composites via Surface-Initiated ICAR ATRP Mediated by Mussel-Inspired Polydopamine Chemistry. <i>Industrial &amp; Engineering Chemistry Research</i> , 2017, 56, 11467-11476.	1.8	9
44	Fluorescence sensor array based on amino acids-modulating quantum dots for the discrimination of metal ions. <i>Analytica Chimica Acta</i> , 2017, 985, 175-182.	2.6	45
45	Controlled Architecture of Hybrid Polymer Nanocapsules with Tunable Morphologies by Manipulating Surface-Initiated ARGET ATRP from Hydrothermally Modified Polydopamine. <i>Chemistry of Materials</i> , 2017, 29, 10212-10219.	3.2	30
46	Microplasma-assisted rapid, chemical oxidant-free and controllable polymerization of dopamine for surface modification. <i>Polymer Chemistry</i> , 2017, 8, 4388-4392.	1.9	38
47	A smartphone readable colorimetric sensing platform for rapid multiple protein detection. <i>Analyst, The</i> , 2017, 142, 3177-3182.	1.7	45
48	Fluorescence sensor array based on amino acid derived carbon dots for pattern-based detection of toxic metal ions. <i>Sensors and Actuators B: Chemical</i> , 2017, 241, 1324-1330.	4.0	139
49	New short-channel SBA-15 mesoporous silicas functionalized with polyazamacrocyclic ligands for selective capturing of palladium ions in HNO <sub>3</sub> media. <i>RSC Advances</i> , 2016, 6, 66537-66547.	1.7	17
50	Surface-Initiated ARGET ATRP of Poly(Glycidyl Methacrylate) from Carbon Nanotubes via Bioinspired Catechol Chemistry for Efficient Adsorption of Uranium Ions. <i>ACS Macro Letters</i> , 2016, 5, 382-386.	2.3	105
51	Time-resolved phosphorescent sensor array based on quantum dots for recognition of proteins. <i>Sensors and Actuators B: Chemical</i> , 2016, 233, 17-24.	4.0	16
52	Multidimensional colorimetric sensor array for discrimination of proteins. <i>Biosensors and Bioelectronics</i> , 2016, 86, 56-61.	5.3	66
53	A nanoplasmonic probe as a triple channel colorimetric sensor array for protein discrimination. <i>Analyst, The</i> , 2016, 141, 4014-4017.	1.7	33
54	Ratiometric fluorescence sensor arrays based on quantum dots for detection of proteins. <i>Analyst, The</i> , 2016, 141, 2046-2052.	1.7	34

#	ARTICLE	IF	CITATIONS
55	Surface-initiated SET-LRP mediated by mussel-inspired polydopamine chemistry for controlled building of novel core-shell magnetic nanoparticles for highly-efficient uranium enrichment. <i>Polymer Chemistry</i> , 2016, 7, 2427-2435.	1.9	50
56	Single nanoporous gold nanowire as a tunable one-dimensional platform for plasmon-enhanced fluorescence. <i>Chemical Communications</i> , 2016, 52, 1808-1811.	2.2	26
57	Charge-Transfer Reactions at the Interface between Atmospheric- Pressure Microplasma Anode and Ionic Solution. <i>Wuli Huaxue Xuebao/ Acta Physico - Chimica Sinica</i> , 2015, 31, 1215-1218.	2.2	6
58	Microplasma-assisted rapid synthesis of luminescent nitrogen-doped carbon dots and their application in pH sensing and uranium detection. <i>Nanoscale</i> , 2015, 7, 20743-20748.	2.8	86
59	Multidimensional Sensor for Pattern Recognition of Proteins Based on DNA-Gold Nanoparticles Conjugates. <i>Analytical Chemistry</i> , 2015, 87, 3354-3359.	3.2	89
60	Atmospheric-pressure microplasma as anode for rapid and simple electrochemical deposition of copper and cuprous oxide nanostructures. <i>RSC Advances</i> , 2015, 5, 62619-62623.	1.7	13
61	Aptamer-Based Plasmonic Sensor Array for Discrimination of Proteins and Cells with the Naked Eye. <i>Analytical Chemistry</i> , 2013, 85, 6571-6574.	3.2	114
62	Lab-on-graphene: graphene oxide as a triple-channel sensing device for protein discrimination. <i>Chemical Communications</i> , 2013, 49, 81-83.	2.2	77
63	Protein Discrimination Using Fluorescent Gold Nanoparticles on Plasmonic Substrates. <i>Analytical Chemistry</i> , 2012, 84, 4258-4261.	3.2	88
64	Self-assembly into magnetic Co <sub>3</sub> O <sub>4</sub> complex nanostructures as peroxidase. <i>Journal of Materials Chemistry</i> , 2012, 22, 527-534.	6.7	116
65	Glucosan controlled biomineralization of SrCO <sub>3</sub> complex nanostructures with superhydrophobicity and adsorption properties. <i>Journal of Materials Chemistry</i> , 2011, 21, 8734.	6.7	32
66	MgCO <sub>3</sub> ·3H <sub>2</sub> O and MgO complex nanostructures: controllable biomimetic fabrication and physical chemical properties. <i>Physical Chemistry Chemical Physics</i> , 2011, 13, 5047-5052.	1.3	45
67	Improved performances of Ni(OH) <sub>2</sub> @reduced-graphene-oxide in Ni-MH and Li-ion batteries. <i>Chemical Communications</i> , 2011, 47, 3159.	2.2	126
68	Shape controlled synthesis of superhydrophobic zinc coordination polymers particles and their calcination to superhydrophobic ZnO. <i>Journal of Materials Chemistry</i> , 2011, 21, 8633.	6.7	33
69	Cu <sub>2</sub> O@reduced graphene oxide composite for removal of contaminants from water and supercapacitors. <i>Journal of Materials Chemistry</i> , 2011, 21, 10645.	6.7	200
70	Mg(OH) <sub>2</sub> Complex Nanostructures with Superhydrophobicity and Flame Retardant Effects. <i>Journal of Physical Chemistry C</i> , 2010, 114, 17362-17368.	1.5	87
71	Ag <sub>2</sub> Se complex nanostructures with photocatalytic activity and superhydrophobicity. <i>Nano Research</i> , 2010, 3, 863-873.	5.8	55
72	Electro-optical Gas Sensor Based on a Planar Light-Emitting Electrochemical Cell Microarray. <i>Small</i> , 2010, 6, 1897-1899.	5.2	3