

Camillo D'Arcangelo

List of Publications by Year in descending order

Source: <https://exaly.com/author-pdf/8555079/publications.pdf>

Version: 2024-02-01

43
papers

1,558
citations

279701

23
h-index

302012

39
g-index

43
all docs

43
docs citations

43
times ranked

1724
citing authors

#	ARTICLE	IF	CITATIONS
1	Thermal cycling for restorative materials: Does a standardized protocol exist in laboratory testing? A literature review. <i>Journal of the Mechanical Behavior of Biomedical Materials</i> , 2014, 29, 295-308.	1.5	238
2	The effect of resin cement film thickness on the pullout strength of a fiber-reinforced post system. <i>Journal of Prosthetic Dentistry</i> , 2007, 98, 193-198.	1.1	142
3	Clinical Comparison of Platelet-Rich Fibrin and a Gelatin Sponge in the Management of Palatal Wounds After Epithelialized Free Gingival Graft Harvest: A Randomized Clinical Trial. <i>Journal of Periodontology</i> , 2016, 87, 103-113.	1.7	88
4	A preliminary study of healing of diode laser versus scalpel incisions in rat oral tissue: a comparison of clinical, histological, and immunohistochemical results. <i>Oral Surgery Oral Medicine Oral Pathology Oral Radiology and Endodontics</i> , 2007, 103, 764-773.	1.6	83
5	Wear properties of dental ceramics and porcelains compared with human enamel. <i>Journal of Prosthetic Dentistry</i> , 2016, 115, 350-355.	1.1	80
6	An evaluation of the action of different root canal irrigants on facultative aerobic-anaerobic, obligate anaerobic, and microaerophilic bacteria. <i>Journal of Endodontics</i> , 1999, 25, 351-353.	1.4	77
7	Clinical evaluation on porcelain laminate veneers bonded with light-cured composite: results up to 7 years. <i>Clinical Oral Investigations</i> , 2012, 16, 1071-1079.	1.4	76
8	Evaluation of a New Nickel-Titanium System to Create the Glide Path in Root Canal Preparation of Curved Canals. <i>Journal of Endodontics</i> , 2013, 39, 1581-1584.	1.4	62
9	Fracture Resistance and Deflection of Pulpless Anterior Teeth Restored with Composite or Porcelain Veneers. <i>Journal of Endodontics</i> , 2010, 36, 153-156.	1.4	55
10	Effect of three surface treatments on the adhesive properties of indirect composite restorations. <i>Journal of Adhesive Dentistry</i> , 2007, 9, 319-26.	0.3	46
11	Effect of Surface Treatments on Tensile Bond Strength and on Morphology of Quartz-fiber Posts. <i>Journal of Endodontics</i> , 2007, 33, 264-267.	1.4	45
12	Bacteriologic Evaluation of the Effect of Nd:YAG Laser Irradiation in Experimental Infected Root Canals. <i>Journal of Endodontics</i> , 2002, 28, 276-278.	1.4	44
13	The Influence of Luting Systems on the Microtensile Bond Strength of Dentin to Indirect Resin-based Composite and Ceramic Restorations. <i>Operative Dentistry</i> , 2009, 34, 328-336.	0.6	42
14	Influence of Surface Treatments on the Flexural Properties of Fiber Posts. <i>Journal of Endodontics</i> , 2007, 33, 864-867.	1.4	40
15	Five-year retrospective clinical study of indirect composite restorations luted with a light-cured composite in posterior teeth. <i>Clinical Oral Investigations</i> , 2014, 18, 615-624.	1.4	40
16	Use of MTA for orthograde obturation of nonvital teeth with open apices: report of two cases. <i>Oral Surgery Oral Medicine Oral Pathology Oral Radiology and Endodontics</i> , 2007, 104, e98-e101.	1.6	34
17	In Vitro Fracture Resistance and Deflection of Pulpless Teeth Restored with Fiber Posts and Prepared for Veneers. <i>Journal of Endodontics</i> , 2008, 34, 838-841.	1.4	34
18	An evaluation of luting agent application technique effect on fibre post retention. <i>Journal of Dentistry</i> , 2008, 36, 235-240.	1.7	33

#	ARTICLE	IF	CITATIONS
19	Effect of Application Technique of Luting Agent on the Retention of Three Types of Fiber-reinforced Post Systems. <i>Journal of Endodontics</i> , 2007, 33, 1378-1382.	1.4	31
20	Treatment of Supra-Alveolar-Type Defects by a Simplified Papilla Preservation Technique for Access Flap Surgery With or Without Enamel Matrix Proteins. <i>Journal of Periodontology</i> , 2013, 84, 1100-1110.	1.7	28
21	Autogenous Periosteal Barrier Membranes and Bone Grafts in the Treatment of Periodontal Intrabony Defects of Single-Rooted Teeth: A 12-Month Reentry Randomized Controlled Clinical Trial. <i>Journal of Periodontology</i> , 2010, 81, 1587-1595.	1.7	26
22	Mechanical Properties of Elastomeric Impression Materials: An In Vitro Comparison. <i>International Journal of Dentistry</i> , 2015, 2015, 1-8.	0.5	25
23	Protocol for a new concept of no-prep ultrathin ceramic veneers. <i>Journal of Esthetic and Restorative Dentistry</i> , 2018, 30, 173-179.	1.8	25
24	Lateral Sinus Floor Elevation Performed with Trapezoidal and Modified Triangular Flap Designs: A Randomized Pilot Study of Post-Operative Pain Using Thermal Infrared Imaging. <i>International Journal of Environmental Research and Public Health</i> , 2018, 15, 1277.	1.2	25
25	The influence of adhesive thickness on the microtensile bond strength of three adhesive systems. <i>Journal of Adhesive Dentistry</i> , 2009, 11, 109-15.	0.3	18
26	Shear bond strength of glass ionomer and resin-based cements to different types of zirconia. <i>Journal of Esthetic and Restorative Dentistry</i> , 2020, 32, 806-814.	1.8	15
27	Canal shaping of different single-file systems in curved root canals. <i>Journal of Dental Sciences</i> , 2017, 12, 328-332.	1.2	13
28	No-Prep Rehabilitation of Fractured Maxillary Incisors with Partial Veneers. <i>Journal of Esthetic and Restorative Dentistry</i> , 2016, 28, 351-358.	1.8	12
29	Effect of Fiber Posts on Stress Distribution of Endodontically Treated Upper Premolars: Finite Element Analysis. <i>Nanomaterials</i> , 2020, 10, 1708.	1.9	11
30	Adhesive Cementation of Indirect Composite Inlays and Onlays: A Literature Review. <i>Compendium of Continuing Education in Dentistry (Jamesburg, NJ)</i> : 1995), 2015, 36, 570-7; quiz 578.	0.1	10
31	Influence of curing time, overlay material and thickness on three light-curing composites used for luting indirect composite restorations. <i>Journal of Adhesive Dentistry</i> , 2012, 14, 377-84.	0.3	9
32	Effect of different conditioning/deproteinization protocols on the bond strength and degree of conversion of self-adhesive resin cements applied to dentin. <i>International Journal of Adhesion and Adhesives</i> , 2018, 81, 98-104.	1.4	7
33	The effect of zoledronate-containing primer on dentin bonding of a universal adhesive. <i>Journal of the Mechanical Behavior of Biomedical Materials</i> , 2018, 77, 199-204.	1.5	7
34	Evaluation of the Effect of Air Polishing With Different Abrasive Powders on the Roughness of Implant Abutment Surface: An In Vitro Study. <i>Journal of Oral Implantology</i> , 2019, 45, 202-206.	0.4	7
35	Retrospective clinical evaluation of a no-prep porcelain veneer protocol. <i>Journal of Prosthetic Dentistry</i> , 2023, 129, 40-48.	1.1	6
36	Safe clinical technique for increasing the occlusal vertical dimension in case of erosive wear and missing teeth. <i>Clinical Case Reports (discontinued)</i> , 2021, 9, e04747.	0.2	6

#	ARTICLE	IF	CITATIONS
37	Antibacterial and Antibiofilm Properties of Three Resin-Based Dental Composites against <i>Streptococcus mutans</i> . <i>Materials</i> , 2022, 15, 1891.	1.3	5
38	NF- κ B and NOS may play a role in human RPMI-8402 cell apoptosis. <i>Cell Biology International</i> , 2005, 29, 529-536.	1.4	4
39	Split crest technique for implant treatment of agenesis of the upper lateral incisors: results of a randomized pilot histological and clinical study at 24-month follow-up. <i>Brazilian Oral Research</i> , 2020, 34, e118.	0.6	4
40	Effect of Light-Sources and Thicknesses of Composite Onlays on Micro-Hardness of Luting Composites. <i>Materials</i> , 2021, 14, 6849.	1.3	3
41	Periodontal Healing of a Human Intrabony Defect Treated by Autogenous Periosteal Barrier Membrane and Bone Graft: A Clinical and Histologic Case Report. <i>Clinical Advances in Periodontics</i> , 2012, 2, 162-170.	0.4	1
42	Capacity of coronal dentin to increase fiberglass post retention: a pull-out test. <i>American Journal of Dentistry</i> , 2005, 18, 307-10.	0.1	1
43	Evaluation of in vitro push-out bond strengths of different post-luting systems after artificial aging. <i>Minerva Dental and Oral Science</i> , 2017, 66, .	0.5	0